



Exhibit B

Weight Percents

Example 8

Wt%	Test		US 6,060,168
	As prepared	w/o Sb ₂ O ₃	Example 8
SiO ₂	62.62	63.5	63.5
Al ₂ O ₃	18.67	18.9	18.9
B ₂ O ₃	8.28	8.4	8.4
MgO	2.95	3.0	3.0
CaO	6.08	6.2	6.2
Sb ₂ O ₃	1.34	-	-

Example 9

Wt%	Test		US 6,060,168
	As prepared	w/o Sb ₂ O ₃	Example 9
SiO ₂	61.81	62.7	62.7
Al ₂ O ₃	18.46	18.7	18.7
B ₂ O ₃	8.19	8.3	8.3
MgO	2.19	2.2	2.2
CaO	6.09	6.2	6.2
SrO	1.88	1.9	1.9
Sb ₂ O ₃	1.32	-	-

Example 10

Wt%	Test		US 6,060,168
	As prepared	w/o Sb ₂ O ₃	Example 10
SiO ₂	61.30	62.1	62.1
Al ₂ O ₃	18.28	18.5	18.5
B ₂ O ₃	8.10	8.2	8.2
MgO	2.17	2.2	2.2
CaO	6.03	6.1	6.1
BaO	2.75	2.8	2.8
Sb ₂ O ₃	1.31	-	-

Example 15

Wt%	Test		US 6,060,168
	As prepared	w/o Sb ₂ O ₃	Example 15
SiO ₂	61.67	62.5	62.5
Al ₂ O ₃	16.93	17.2	17.2
B ₂ O ₃	11.55	11.7	11.7
CaO	8.46	8.6	8.6
Sb ₂ O ₃	1.32	-	-